


# Technical Data Sheet

## SUNCURE MCDEA

### Description



Chemical Name 4,4'-Methylene-bis-(3-chloro-2,6-diethylaniline)  
 CAS # 106246-33-7

Formula  $C_{21}H_{28}Cl_2N_2$   
 Mol. wt. 379.366

### Specifications

Item	Specification
Appearance	Off-white to white pellet
Melting Point (°C)	87 ~ 89
Moisture (%)	Max. 0.15
Purity (%)	Min. 98.0

### Applications

PU elastomers with excellent properties can be prepared in combination with TDI prepolymers. And it can improve the performance of PU Elastomers and show a good additive effect in the PU Casting, Spraying, RIM and other process technology methods, as well as microporous products, TPU, adhesives, coating agents and other products are widely used in preparation.

### Delivery & Storage

Package 25kg cardboard drum

Storage Keep containers closed when not in use. Use proper handling precautions designated for a moisture-sensitive substance.